

# Reflectix® Insulation

## Technical Information DB1

### Double Foil, Double Bubble, Foil Both Sides

Reflectix® Insulation consists of two outer layers of aluminum foil reflect 97% of radiant heat. Each layer of foil is bonded to a tough layer of polyethylene for strength. Two inner layers of insulating bubbles resist conductive heat flow while a center layer of polyethylene gives Reflectix® high reliability and strength.

#### Technical Data:

Temperature Range:	-60 degrees to +180 degrees F
Nominal Thickness:	5/16 inch (.312)
Weight:	.81612 oz./sq. ft.
Flame Spread Index (ASTM E 84):	Less than 75
Smoke Developed Index (ASTM E 84):	Less than 450
Fire Rating:	Class C
Linear Shrinkage:	None
Reflectance (IR):	97%
Water Vapor Transmission (ASTM E 96):	0.02
Puncture Resistance:	60 lb./in.
Mold and Mildew:	No Growth
Emittance:	0.03
Tensile Strength:	3.7 N/mm
Pliability:	No Cracking
Hot Surface Performance:	Passed

Reflectix, Inc. #1 School Street (P.O. Box 108) Markleville, IN 46056  
Ph: (800) 879-3645 (US/Can) or (765) 533-4332 • Fax: (765) 533-2327  
www.reflectixinc.com • Email: customerservice@reflectixinc.com

[www.youtube.com/ReflectixInsulation](http://www.youtube.com/ReflectixInsulation) • "Like Us" at [www.facebook.com/ReflectixInsulation](http://www.facebook.com/ReflectixInsulation) • [www.pinterest.com/reflectixinc](http://www.pinterest.com/reflectixinc)